



**ROHOŽNIK
WHITE**

Danucem Slovensko a.s. T +421 34 77 65 111
906 38 Rohožník F +421 34 77 65 149
Slovakia www.crh-white.com

PORTLAND CEMENT - WHITE CEM II/A-S 52,5 N - (EN 197-1)

Rohožník White

<u>Control Period / Überwachungszeitraum</u>		2021
<u>Fineness / Feinheit</u>		
Specific surface / Spezifische Oberfläche	cm ² /g	4000 - 4600
Residue on 0,045 mm sieve / Siebrückstand, Sieb 0,045 mm	%	1,0 - 4,0
<u>Soundness (Expansion/ Le Chat) / Dehnungsmass (Le Chat.)</u>		
	mm	0,5 - 1,5
<u>Water demand / Wasseranspruch</u>		
	%	27,0 - 32,0
<u>Setting time / Erstarrungszeiten</u>		
Initial / Erstarrungsbeginn	Min.	100 - 150
Final / Erstarrungsende	Min.	140 - 200
<u>Compressive strenght / Druckfestigkeit</u>		
at 2 days / nach 2 Tagen	N/mm ²	27,0 - 35,0
at 28 days / nach 28 Tagen	N/mm ²	58,0 - 65,0
<u>Chemical specifications / Chemische Spezifikationen</u>		
Insoluble residue / Unlöslicher Rückstand	%	0,5 - 1,0
Cl ⁻	%	< 0,1
Na ₂ O- equivalent / Äquivalent	%	< 0,6
SO ₃	%	2,3 - 3,0
Whiteness / Hellbezugswert Ry:	%	80,0 - 83,0
Specific gravity / Rohdichte (ca.):	kg/ dm ³	3,10
Bulk density / Schüttdichte (ca.):	kg/ dm ³	1,05

Rohožník (SK), October 1th, 2021



Quality Manager signature