



**ROHOŽNÍK
WHITE**

CEM II/B-S 42,5 N

White portland slag cement strength class of 42.5 N

White portland slag cement strength class of 42.5 N with a guaranteed minimum strength of 42.5 MPa after 28 days and minimum initial strength of 10.0 MPa after 2 days. White portland cement opens new dimensions in design and construction, with excellent quality, high strength, and aesthetic appearance.

Advantages:

- highest quality and high durability
- excellent functionality and unrivalled appearance
- due to lower development of hydration heat, suitable for summer use
- minimal change in volume
- excellent processability
- excellent compatibility with plastification admixtures
- easy colouring of concrete with pigments
- rapid increase in early strength
- high final compressive strength

Applications:

- white or coloured concrete
- especially suitable for exposed concrete and architectural concrete
- Ready Mix production, and production of transported concrete
- production of plain concrete of higher strength classes and reinforced concrete structures
- plaster and masonry mortar

Manufacturer:

- Danucem Slovensko a.s. Plant Rohožník

Shipping options:

- bulk in tanker trucks • dispatched from: Rohožník Plant

Product marking	Product name	Clinker	Blast Furnace Slag	Additives
CEM II/B-S 42.5 N	White portland slag cement	65 - 79 %	21 - 35 %	0 - 5 %

CEM II/B-S 42.5 N WHITE complies with EN 197-1:2011. TSÚS Bratislava supervises the production. Danucem Slovensko a.s. has established a quality management system according to EN ISO 9001:2015 and an environmental management system according to the EN ISO 14001:2015.

Technical parameters CEM II/B-S 42.5 N WHITE

Parameter	Test method	EN 197-1: 2011	Typical value
SO ₃ content (% wt.)	EN 196-2	≤ 3.5	2.7
Cl ⁻ content (% wt.)	EN 196-2	≤ 0.1	0.01
Volume stability (mm)	EN 196-3	≤ 10	0.5
Setting time (min.)	EN 196-3	≥ 60	140
Compressive strength in 2 days (MPa)	EN 196-1	≥ 10.0	29.0
Compressive strength in 28 days (MPa)	EN 196-1	≥ 42.5 ≤ 62.5	58.0

CEM II/B-S 42.5 N WHITE meets the requirements of Decree No. 275/2004 on Reduced Cr⁶⁺ Content.

The average values given in the Product Data Sheet are purely informative and may differ from specific samples.



DUNAJ

DUNA

DONAU

DANUBE

For further information or sales and technical contact
please visit www.danucem.com